
SPECIFICATION FOR THE APPLICATION OF STARWOOD A. F.1®

Painting of (1)_____

The treatment will be made by (2)_____ application of
fire-retardant impregnating STARWOOD A. F.1®.

The application cycle provides the following procedures:

1) PREPARATION OF THE SURFACES

Verify that the materials to protect are free of grease, fats, oil, waxy impregnating and preexisting varnishes. Existing paint coats must be removed by sandblasting or by sandpapering with coarse grain and then fine abrasive paper at naked wood.

After this operation, in order to ensure maximum adherence of fire-retardant paint on the support, carry out further cleaning using a dampened cloth with nitro thinner to remove completely from wood traces of wax.

It should be checked carefully that the humidity of the wooden materials to coated is less than the value of 12% in weight.

If the conditions of preparation above indicated are not respected, we don't give any guarantee of durability of treatment.

2) FIRE RETARDANT IMPREGNATING AGENT

Application of 4 coats of 125 g/m² each or of 5 coats of 100 g/m² each for a total consumption of applied product equal to 500 g/m².

For all information that aren't present in this specification for the application, look at data sheet.

-
- 1) Indicate the type of wood support to treat (wall, matchboard, false ceiling, etc.) and the quality of the wood used (fir, beech, oak, etc.)
 - 2) Indicate the application system used (spray, brush, roller, etc.)
-